

RUNO SP¹

POLYESTER NONWOVEN CARRIERS
FOR BITUMINOUS MEMBRANES



Area weight, g/m ²	Tensile strength MD/CD, N/50mm	Elongation at brake MD/CD, %	Shrinkage MD/CD, %	Thickness, mm
ISO 9073-1	ISO 9073-3		DIN 18192	ISO 9073-2
100	310/190	20/25	≤2,0/≤-2,0	0,75
110	340/200	22/28	≤2,0/≤-2,0	0,80
120	420/240	25/30	≤2,0/≤-2,0	0,85
130	460/260	25/30	≤2,0/≤-2,0	0,90
140	520/300	27/32	≤2,0/≤-2,0	0,95
150	570/330	27/32	≤2,0/≤-2,0	1,00
160	620/350	27/32	≤2,0/≤-2,0	1,05
170	670/370	27/32	≤2,0/≤-2,0	1,10
180	720/400	28/34	≤2,0/≤-2,0	1,15
190	750/430	28/34	≤2,0/≤-2,0	1,20
200	780/460	29/34	≤2,0/≤-2,0	1,25
210	810/500	29/34	≤2,0/≤-2,0	1,30
220	840/550	29/34	≤2,0/≤-2,0	1,35
230	870/600	29/34	≤2,0/≤-2,0	1,40
240	885/625	29/34	≤2,0/≤-2,0	1,45
250	900/650	29/34	≤2,0/≤-2,0	1,50
260	925/670	29/34	≤2,0/≤-2,0	1,55
270	950/700	29/34	≤2,0/≤-2,0	1,60
300	1000/750	30/36	≤2,0/≤-2,0	1,70
330	1050/800	30/36	≤2,0/≤-2,0	1,80

Tolerances: Area weight -5 %
Tensile strength -10 %
Elongation at break -15 %
Thickness ±15 %

AQUAIZOL LLC
Identification code: 31466053
Registered office: 47-B Symsky Shliakh St.,
Podvirky, Kharkiv region, 62371 Ukraine
Phone: +38 (057) 765-02-54

¹SP – spunbond technology, non-reinforced